

Al-Mahaba EVA 2018 - Technical Data Sheet

18.2% Ethylene - Vinyl Acetate [EVA] copolymer

Product description: Al-Mahaba EVA 2018 is an 18.2% ethylene - vinyl acetate copolymer resin, designed

for a variety of foam moulding application; manufactured by Al-Mahaba for plastic industries

in Arab Republic of Egypt using Sipchem EVA resin.

EVA 2018 exhibits low melting temperature, good processability and mechanical

properties.

Applications: Foams, Shoe Soles, Injection Moulding, Profile Extrusion, Films and Compounds

Resin properties:

Physical properties	Typical Value ¹	Unit	Test Method
Melt Index (190°C / 2.16 kg)	2.0	g/10 min	ASTM D1238
Vinyl Acetate Content	18.2	wt%	IPC Method
Density	0.935	g/cm ³	IPC Method
Vicat Softening Point	64	°C	ASTM D1525
Melting Point	87	°C	IPC Method
Tensile Strength at Yield	5.2	MPa	ASTM D638
Tensile Strength at Break	11	MPa	ASTM D638
Elongation at Yield	260	%	ASTM D638
Elongation at Break	>800	%	ASTM D638
Flexural Modulus	60	MPa	ASTM D790
Hardness Shore A	76		ASTM D2240
Hardness Shore D	36		ASTM D2240

^{1.} These are typical properties: these are not to be construed as specifications.

AL-MAHABA FOR PLASTIC INDUSTRIES

Industrial Zone A1, Plot XIO 10th of Ramadan city, Al Sharkia governorate TEL: 00201280899911 - 00201272800056

The preliminary information in this document is provided for pre-marketing purposes only, and relates only to the named product or materials when not in combination with any other product or materials. The information and recommendations presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made. Before using one of the products mentioned herein, customers and other users should take care in determining the suitability of such product for the intended use. Almahaba and International Polymers Company therefore, do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein.

^{2.} This product is not intended for use in medical applications and should not be used in any such applications

^{3.} Contact your Sipchem Representative for potential food contact application compliance.